

THE CALCINATED PETROLEUM COKE

TŞ 05766698-17-99

№	Description of index	Figure	
		A	B
1	Mass portion of the total moisture, %, not more than	0,5	0,5
2	Ash content, %, not more than	0,7	0,6
3	Mass portion of sulfur, in %, not more than	1,0	0,8
4	Real density, g/ sm ³ ,	2,01-2,06	2,06-2,08
5	Mass portion of coke with the size of pieces more than 6 mm, %, not less than	30,0	30,0
6	Mass portion of oiled product	-	0,5

Note:

1. The mass portion of the total moisture is not to rejection indicators at shipment in open semicars and serves for calculation with the consumer.
2. The position № 6 is not rejection. Its share exceeding the established norm is not subject to payment.

КОКС НЕФТЯНОЙ ПРОКАЛЕННЫЙ ДЛЯ ГРАФИТИРОВАННОЙ ПРОДУКЦИИ.

ТШ 05766698-17-99 Изменение № 2,3

№	Наименование показателей	Норма	
		А	Б
1	Массовая доля общей влаги, %, не более	0,5	0,5
2	Зольность, %, не более	0,7	0,6
3	Массовая доля серы, %, не более	1,0	0,8
4	Действительная плотность, г/ на см ³ , в пределах	2,01- 2,06	2,06- 2,08
5	Массовая доля кокса с размером кусков более 6 мм, %, не менее	30,0	30,0
6	Массовая доля обмасливающего продукта, %, не более	Не опред	0,5

ПРИМЕЧАНИЯ:

1. Массовая доля общей влаги не является браковочным показателем при отгрузке в открытых полувагонах и служит для расчета с потребителем.
2. Показатель «Массовая доля обмасливающего продукта» не является браковочным. Доля обмасливающего продукта, превышающая установленную норму, оплате не подлежит.

GRAFITIRLENEN ÖNUM ÜÇİN GYZARDYLAN NEBIT KOKSY

TS 05766698-17-99 Üýtgetme № 2,3

№	Наименование показателей	Norma	
		А	Б
1	Umumy çygyn massalaýyn paýy, %, köp däl	0,5	0,5
2	Küllüligi, %, köp däl	0,7	0,6
3	Kükürdiň massalaýyn paýy, %, köp däl	1,0	0,8
4	Hakyky dykzlygy, g/ sm ³ , çäklerinde	2,01-2,06	2,06-2,08
5	Bölekleriniň ölcegi 6 mm köp koksuh massalaýyn paýy, %, az däl	30,0	30,0
6	Ýaglaýjy önümiň massalaýyn paýy, %, köp däl	kesgitlenmeyär	0,5